

sales@fuelcellstore.com www.fuelcellstore.com

ELAT® Gas Diffusion Layers

We are pleased to offer NuVant's ELAT woven carbon cloth gas diffusion layer (GDL) line. ELAT has been engineered to have state-of-the-art performance over a wide range of operating conditions offering the best of performance at a reasonable price.

Suggest Uses:

- Fuel Cells
- Electrolysis
- Flow through Batteries
- Water clean-up Electrochemistry
- And more!

El	44

Property	Value	Hydrophilic	ELAT LT1400	ELAT LT2400
Thickness	micron	406	454	490
Areal Density	g/cm²	0.013	0.017	0.025
Volumetric Density	g/cm³	0.346	0.377	0.8
Electrical Conductivity*	mΩcm²	TBD	TBD	TBD
Air Permeance	L/(m²*sec*Pa)	2.156	0.104	10 ml/(cm ² *sec)
Porosity	%	80	62-64	31 microns
Carbon Content**	%	99.5	99.5	99.5
Microporous Layer	N/A	No	Single Sided	Double Sided
Web Material	N/A	Woven Cloth	Woven Cloth	Woven Cloth

** In woven, variable in coating for hydrophobicity

Catalyzed ELAT also available with a typical two to three day lead time.