

SIGRACET[®] GDL 36BB

Gas Diffusion Layers for PEM Fuel Cells and Electrolyzers

Material Properties

Properties	Units	Range
Areal weight ¹⁾	g/m ²	105 ± 10
(@ 5 psi load) ²⁾		285 ± 25
Thickness (@ 1 MPa load) ²⁾	µm	240 ± 20
TP El. Resistance (@ 1 MPa load) ³⁾	mΩ x cm ²	< 12
IP Pressure Drop (@ 1MPa load) ⁴⁾	bar	< 0,8

Specified material properties are printed in bold. Additional data presented is provided for information purposes only

Abbreviation/Units: TP = Through plane; IP = In plane; 5 psi = 0.0345 MPa

Note: Values based on the average values measured on ring-shaped samples with inner-/outerdiameter (12/40)mm over the width of the roll and a 2-sigma normal distribution with a 95,4% confidence interval.

¹⁾ Internal, based on DIN EN ISO 536

²⁾ Internal, based on DIN EN ISO 9073

³⁾ Internal, based on DIN 51911

⁴⁾ Internal, based on Darcy's Law @ 0,5 slpm

® registered trademarks of SGL CARBON SE

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should therefore not be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our "General Conditions of Sale".