

Aquivion® E98-15S

perfluorosulfonic acid

Aquivion® E98-15S is a chemically-stabilized (denoted by S-suffix) perfluorosulfonic acid (PFSA) ionomer membrane that exhibits an Equivalent Weight (EW) of 980 g/eq. Nominal thickness is 150 microns.

Aquivion® PFSA ionomer membranes are melt-extruded products based on the unique Short Side Chain copolymer of Tetrafluoroethylene (TFE) and Sulfonyl Fluoride Vinyl Ether (SFVE) $F_2C=CF-O-CF_2CF_2-SO_2F$ produced by Solvay. They are available in the acid form and feature a lower

Equivalent Weight (EW) than most commercial proton exchange membranes. The unique Short Side Chain copolymer allows higher crystallinity, improved mechanical properties and better proton conductivity.

Typical applications include PEM fuel cells, water electrolyzers, separators for hydrogen or redox flow batteries, and pervaporation or gas humidification systems.

Please visit Aquivion.com for more information.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America

Physical

	Typical Value	Unit	Test method
Density - 23°C, 50%R.H.	1.93	g/cm ³	Internal Method
Equivalent Weight (EW) ¹	980	g/eq	Internal Method
Membrane ²			
Thickness	150.0	µm	
Weight	290	g/m ²	
Total Acid Capacity	> 1.00	meq/g	Internal Method

Mechanical

	Typical Value	Unit	Test method
Tensile Modulus	270	MPa	
Tensile Stress ³			ASTM D882
MD : Break	40.0	MPa	
TD : Break	30.0	MPa	
Elongation ³			ASTM D882
MD : Break	150	%	
TD : Break	200	%	

Electrical

	Typical Value	Unit	Test method
Conductivity ⁴	> 160	mS/cm	Internal Method

Additional Information

	Typical Value	Unit	Test method
Water Uptake Properties (in liquid) ⁵			Internal Method
By weight	< 30	%	
Elongation (MD)	< 15	%	
Elongation (TD)	< 20	%	

Aquivion® E98-15S

perfluorosulfonic acid

HEALTH, SAFETY AND ENVIRONMENT

- Aquivion® PFSA membranes are not harmful if used and handled according to standard processing procedures (see for example the "Guide to the Safe Handling of Fluoropolymer Resins" issued by the Society of the Plastics Industry). If handled inappropriately, membranes may release harmful toxic chemicals. Please refer to the Material Safety Data Sheets for more information on handling and safety.

PACKAGING, SHIPMENT AND STORAGE

- The membranes are usually available in sheets of customized formats or rolls in various lengths (dimensions are based on dry product conditioned at 23 °C and 50 % Relative Humidity). They are sealed in an inert environment with a multilayer protection film before packaging inside a shock-protected cardboard box. It is recommended to store the product in a clean, controlled humidity environment and protected from direct sun light or other sources of heat.
-

Notes

Typical properties: these are not to be construed as specifications.

¹ eq = (mol SO₃H)

² 23°C, 50% R.H.

³ Measured on E98-05S at 23°C, 50% R.H.

⁴ Setup: 4-probe, in-plane measurement; Procedure: set T_{cell} = 80°C, T_{gas} = 90°C, Humidity 100%, Flow 800 sccm.

⁵ 4-hour soak in liquid at 100°C

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2020 Solvay Specialty Polymers. All rights reserved.

